

# Schematic Representation for Illustrating the Procedure of Optical Noise Figure in Erbium-doped Fiber Amplifier (EDFA) and Praseodymium-doped Fiber Amplifier (PDFA)

Abdel Hakeim M. Husein and Fady I. EL-Nahal

**Abstract**—The erbium-doped fiber amplifier (EDFA) operating at 1530 nm wavelength and the praseodymium-doped fiber amplifier (PDFA) at 1300 nm wavelength are promising components for optical fiber communications due to their high gain, high saturation powers, low noise and low crosstalk. In this paper, using comprehensive models which take into account the spectroscopic properties of the fiber amplifiers, we have analyzed the temperature-dependent noise figure effects on both EDFAs and PDFAs.

**Index Terms**—EDFA, PDFA, gain, noise, noise figure.

## I. INTRODUCTION

RARE earth doped fiber amplifiers and lasers are important tools in understanding and designing new optical devices. EDFAs are attractive devices for single-mode fibers in optical communication systems in the 1530 nm wavelength band which is known as a third window for fiber optic communication. EDFAs have many advantages such as high gain and low noise in optical communication networks.

EDFAs are characterized by gain which depends on temperature and this feature is very interesting in the modern optical transmission systems which use wavelength division multiplexing (WDM) [1]. Various temperature values in published works have then been used to experimentally find the gain at optimum amplifier lengths by analytical solution of the rate equation derivation [2–5]. The temperature-dependent gain and noise figure (NF) in EDFAs have been studied theoretically and experimentally for 980 nm and 1480 nm with the EDFAs of different lengths. These results have shown that the NF is temperature dependent [6].

Praseodymium  $\text{Pr}^{3+}$ -doped fiber amplifiers (PDFAs) are now attracting more interest, because they expected to play a vital role in upgrading 1300 nm optical systems that are used

in almost all terrestrial optical telecommunication networks [7]. PDFAs have the quantum efficiency of the  $^1\text{G}_4 \rightarrow ^3\text{H}_5$  of the transition in the 1300 nm wavelength region [8–11]. For this point, the low-phonon-energy glass hosts are needed to examine the amplifier span and all optical link-capacity.

Recently, some efforts have been methodically made to develop these types of optical amplifiers for utilizing over a wide range of temperatures. Especially, one major issue of PDFA research is to develop the gain efficiency with low NF of PDFA using ZBLAN ( $\text{ZrF}_4$ ,  $\text{BaF}_2$ ,  $\text{LaF}_3$ ,  $\text{AlF}_3$ ,  $\text{NaF}$ ) fluoride, sulfide ( $\text{GeGaS}$ ) and some borate-based glasses as a host material [12–15]. In addition, the temperature dependence of the gain characteristics of PDFAs is critical for these systems.

In this work, we have compared the noise figure of EDFA and PDFA amplifiers after solving the rate equation by including the temperature effect observed on the transitions. The numerical results are given for both EDFA and PDFA amplifiers, operating at the 1530 nm and 1300 nm signal wavelengths respectively. EDFAs are widely used in the third window so a wider band WDM that would cover the band from 1300 to 1550 nm can be achieved [8]. The great interest in PDFA amplifiers results from the fact that an important part of the fiber optic network worldwide uses the 1300 nm second communication window. The variation of NF over the temperature range  $-20^\circ\text{C}$  to  $+60^\circ\text{C}$  was studied for different amplifier lengths.

## II. SCHEMATIC REPRESENTATION OF NF

This work will give understanding of the physical concept of two and four level fiber amplifiers and obtaining the noise figure of the signals at different temperature range by using rate equation technique. The energy levels amplification mechanism for erbium  $\text{Er}^{3+}$  and praseodymium  $\text{Pr}^{3+}$  ions doped in glass hosts are shown in Fig. 1 and Fig. 2 respectively.

The single-mode fiber doped  $\text{Er}^{3+}$  ions can be considered homogeneously broadened in a two-level amplification system. Fig. 1 illustrates the energy diagram of erbium ions in glass hosts,  $R_S$  denotes the stimulated absorption and emission rates

A. H. M. Husein is with the Al-Aqsa University, Physics Department, P.O. Box 4051, Gaza, Gaza Strip, Occupied Palestinian Territories (phone: +970(59)9165678; fax: 970(8) 286 5309; e-mail: hakeim00@yahoo.com).

F. I. El-Nahal is with the Islamic University of Gaza, Electrical Engineering Department, Gaza, Gaza Strip, Occupied Palestinian Territories (e-mail: fnahal@iugaza.edu.ps).




Fig. 1. The energy diagram of erbium ions in glass hosts such as silica tellurite and fluorozirconate.




Fig. 2. The energy levels and amplification mechanism for  $\text{Pr}^{3+}$  ions in glass hosts.

associated with the signal between the population inversion densities  $N_1$  and  $N_2$  of the lower (ground) and upper (metastable) levels, respectively, the first and the second (metastable) levels respectively and  $R_p$  refers to both the pumping rate from the first to the third level and the stimulated emission rate between them.  $N_1$ ,  $N_2$  and  $N_3$  are population of  $\text{Er}^{3+}$ -ions in the first, second and third level, respectively.  $\gamma_2$  is the transition probability, which is the sum of the spontaneous radiative and nonradiative transition probabilities from the metastable to the ground level.  $\gamma_{32}$  is the transition probability per unit time for an  $\text{Er}^{3+}$  ion and represents the thermal relaxation from the upper state (third level) to the lower state (second level) [16], then the rate equation can be written as

$$\frac{dN_1}{dt} = -R_p(N_1 - N_3) + \gamma_2 N_2 + R_s(N_2 - N_1) \quad (1)$$

$$\frac{dN_2}{dt} = -R_s(N_2 - N_1) - \gamma_2 N_2 + \gamma_{32} N_3 \quad (2)$$

$$\frac{dN_3}{dt} = R_p(N_1 - N_3) - \gamma_{32} N_3 \quad (3)$$

The rate equations are solved the conditions of steady state, where all of the level populations are time invariant, i.e.  $dN_i/dt = 0$ , ( $i = 1, 2, 3$ ).

$$N_1 = N \frac{R_p \beta + R_s + \gamma_{21}}{R_p(1 + 2\beta) + R_s(2 + \beta) + \gamma_{21}} \quad (4)$$

$$N_1 = N \frac{R_p \beta + R_s + \gamma_{21}}{R_p(1 + 2\beta) + R_s(2 + \beta) + \gamma_{21}} \quad (5)$$

where  $\beta = \frac{N_m}{N_{m-1}} = \exp(-\Delta E_m / k_B T)$  [19] is the Boltzmann's

population relation where  $\Delta E_m = E_m - E_{m-1}$  is the energy difference between the third and the second level,  $k_B$  is the Boltzmann's constant ( $k_B = 1.38 \times 10^{-23} \text{ J/K}$ ), and  $T$  is the temperature in degrees Kelvin [20].

The gain of EDFA amplifier is given by [21]

$$G = \exp[\Gamma_s \sigma_s^a (\eta N_2 - N_1) L] \quad (6)$$

where  $\sigma_s^a$  is the signal absorption cross sections,  $L$  is the length of the fiber,  $\eta$  is the ratio between the signal emission and absorption cross sections and  $\Gamma_s$  is the signal mode overlap factor of the fiber with erbium distribution and dimensionless integral overlap. The amplified spontaneous emission (ASE) is taken into consideration, but the excited state absorption (ESA) effect is neglected for simplicity. The noise figure as a function of the signal gain, input and output ASE spectral densities, in decibel (dB) is given by

$$NF(\text{dB}) = 10 \log_{10} \left( \frac{1}{G} + \frac{P_{ASE}^o(\lambda_s)}{G h \nu_s} - \frac{P_{ASE}^i(\lambda_s)}{h \nu_s} \right) \quad (7)$$

where  $1/G$  is the beat noise,  $P_{ASE}^i$  and  $P_{ASE}^o$  are the amplified input and the amplified output ASE spectral density respectively,  $\nu_s$  is the frequency of the signal wavelength and  $h = 6.626 \cdot 10^{-34} \text{ Js}$  is the Planck constant.

The population of  $\text{Pr}^{3+}$  levels is labeled as  $N_0$ ,  $N_1$ ,  $N_2$ ,  $N_3$ ,  $N_4$  and  $N_5$  respectively, and also the total population density  $N$  is taken as  $N = N_0 + N_1 + N_2 (=N_{21} + N_{22}) + N_3 + N_4 + N_5$ . In this point, the special names of  $N_2$  and  $N_0$  are the population densities of metastable and ground levels, respectively. The amplified spontaneous emission (ASE) is also neglected, as the signal input power was significantly above the equivalent ASE noise power. Also it includes the effect of the signal photon (ESA) to have better accuracy. To calculate all of the population of  $\text{Pr}^{3+}$  at steady state conditions, the effects of pump ESA and the cooperative upconversion are not taken into consideration. On the basis of the energy level diagram shown in Fig. 2, and using upper conditions the rate equation for  $\text{Pr}^{3+}$  population density can be written as follows

$$\frac{dN_3}{dt} = R_p N_0 - R_p N_3 - \gamma_{32} N_3 \quad (8)$$

$$\frac{dN_{22}}{dt} + \frac{dN_{21}}{dT} = R_{0s} N_0 - R_{2s} N_{22} - N_{22} \gamma_{21} + \gamma_{32} N_3 \quad (9)$$

$$\frac{dN_1}{dt} = R_{2s} N_{22} + \gamma_{21} N_{22} - \gamma_{10} N_1 \quad (10)$$

$$\frac{dN_0}{dt} = R_p N_3 - R_p N_0 - R_{0s} N_0 + \gamma_{10} N_1 \quad (11)$$

The rate equations are solved under the conditions of steady state, where all of the level populations are time invariant, i.e.  $dN_i/dt = 0$ , ( $i = 1, 2, 3$ ).

$$N_{22} = N \frac{R_p}{\gamma + R_p(1 + 1/\beta) + R_{2s}} \quad (12)$$

The gain of PDFFA amplifier is given by [20]

$$G = \exp[\Gamma_s \sigma_{2s} N_{22} L] \quad (13)$$

where  $L$  represents the length of  $\text{Pr}^{3+}$ -doped amplifier and  $G$  denotes the signal gain and  $\sigma_{2s}$  is the stimulated emission cross section of transitions. The NF of the amplifier is defined as then degradation in signal-to-noise ratio from input to output of the amplifier, NF in decibel (dB) is given by:

$$NF(\text{dB}) = 10 \log_{10} \left[ \frac{1}{G} \left( 1 + \frac{P_{ase} \Delta \nu}{GP_{in}} \right) + \frac{1}{G} \frac{P_{ase} \Delta \nu}{h \nu_s} \left( 1 + \frac{P_{ase} \Delta \nu}{2GP_{in}} \right) \right] \quad (14)$$

where  $(1/G)$  is the signal-spontaneous beat noise,  $P_{ase}$  is the ASE power density,  $P_{in}$  is the signal power density,  $\nu_s$  is the frequency of the input signal, and  $\Delta \nu$  is the optical linewidth of the amplifier.

### III. RESULTS AND DISCUSSION

The numerical calculations of the approximate expression of the noise figure of EDFA amplifier has been carried out. For simplicity the energy difference between levels of metastable is considered as  $300 \text{ cm}^{-1}$  in the room temperature. The relevant fiber parameters values for an Al/P-silica erbium-doped fiber amplifier Symbols Definitions are shown in Table 1 [21].

For numerical calculation, the fiber parameters for  $\text{Pr}^{3+}$  doped sulfide and ZBLAN amplifiers are taken from [22, 23]. The parameters and their values used in calculation are shown in Table 2. As can be noted from Table 2, the stimulated emission cross section of GeGa-sulfide glass is larger than the cross section of ZBLAN one. The lifetime of the transition  $\tau$  is an important quantity to evaluate the amplifier performance since, if it is short, it then becomes necessary to pump very hard to maintain a population inversion. Here  $\sigma_{03}$  is the stimulated absorption of  $\text{Pr}^{3+}$  transitions  $\nu_p$  and  $\nu_s$  are the pump and signal frequencies respectively,  $P_p$  and  $P_s$  are the pump and signal powers respectively,  $\Gamma_p$  and  $\Gamma_s$  are the overlap factors;  $A_p$  and  $A_s$  are the effective doped areas of the core corresponding to pump and signal powers respectively, and  $h$

TABLE I  
THE RELEVANT FIBER PARAMETERS VALUES FOR AN AL/P-SILICA ERBIUM-DOPED FIBER SYMBOLS DEFINITIONS [21]

Symbol	Definition	Value
$\sigma_s^e$	Signal emission cross- section	$5.7 \times 10^{-25} \text{ m}^2$
$\sigma_s^a$	Signal absorption cross- section	$6.6 \times 10^{-25} \text{ m}^2$
$\sigma_p^e$	Pump emission cross- section	$6.6 \times 10^{-25} \text{ m}^2$
$\sigma_p^a$	Pump absorption cross- section	$2.44 \times 10^{-25} \text{ m}^2$
$\tau$	Life time	10.8 ms
$N$	Erbium concentration	$3.86 \times 10^{24} \text{ m}^{-3}$
$\lambda_s$	Signal wavelength	1530nm
$\lambda_p$	Pump wavelength	1480nm
$\nu_s$	Signal frequency	$1.96 \times 10^{14} \text{ Hz}$
$\nu_p$	Pump frequency	$2.027 \times 10^{14} \text{ Hz}$
$P_{ASE}^+(L)$	Copropagating ASE power	0.15mW
$\alpha_s$	Signal absorption constant	$0.5 \text{ m}^{-1}$
$L$	Fiber length	0 to 45m
$P_p^i$	Input pump power	30mW

TABLE II  
PARAMETERS AND THEIR VALUES USED IN CALCULATIONS FOR THE  $\text{Pr}^{3+}$ -DOPED SULFIDE AND ZBLAN FIBER AMPLIFIERS

Parameters	GeGa-sulfide Ref.[23]	ZBLAN Ref.[24]
$\sigma_{03}$	$9.7 \times 10^{-26} \text{ m}^2$	$4.24 \times 10^{-26} \text{ m}^2$
$\sigma_{2s}$	—	$1.2 \times 10^{-26} \text{ m}^2$
$\tau$	360 $\mu\text{s}$	110 $\mu\text{s}$
$N$	$7.82 \times 10^{25} \text{ m}^{-3}$	$4.80 \times 10^{25} \text{ m}^{-3}$
$\lambda_s$	1310 nm	1300 nm
$\lambda_p$	1028 nm	1017 nm
$A_s, A_p$	$15.40 \mu\text{m}^2, 12.30 \mu\text{m}^2$	$8.04 \mu\text{m}^2$
$\Gamma_s, \Gamma_p$	0.38, 0.40	0.6
$L$	8 m	36 m

is Planck's constant. At room temperature for simplicity, the energy interval between  $N_{22}$  and  $N_{21}$  levels of GeGa-sulfide and ZBLAN-based  $\text{Pr}^{3+}$  ions are assumed to be close to 500 and 400  $\text{cm}^{-1}$ , respectively. The relevant fiber parameters for both EDFA and PDFA models depend on the temperature range  $-20 \text{ }^\circ\text{C}$  to  $+60 \text{ }^\circ\text{C}$ .

#### A. Noise Figure versus Length for $\text{Er}^{3+}$

It was noted from Fig. 3 that the noise figure swiftly increases for 0–6 m length and there is no important effect of temperature dependency at different temperatures, while it is still low at lengths greater than 6 m. There is little noise effect at a variety of temperatures in this region ( $<6 \text{ m}$ ) because the gain and noise figure is low enough due to the length of the EDFA, as a result, the population inversion ratio is very low. If the EDFA length is low enough, the population inversion is very low so that the absorption and emission rates are low but we can find the temperature-dependent gain (temperature-dependent absorption and emission) and noise effect. It was noted that the variation of noise figure via the EDFA length in spectral contribution of copropagating ASE power. For different temperature the NF is nearly the same with some variation for different length up to 45 m.

#### B. Noise Figure versus Length for $\text{Pr}^{3+}$

For both GeGa-sulfide-based and ZBLAN-based  $\text{Pr}^{3+}$ -doped fiber amplifiers over the temperature range from  $-20 \text{ }^\circ\text{C}$  to  $60 \text{ }^\circ\text{C}$ , the variations of noise figure with the length of the amplifier are considered. The results for the GeGa-sulfide based amplifier are shown in Fig. 4 and Fig. 5 respectively. It is obvious from the results that the signal noise figure rises with decreases in the length, at the same time the NF declines when the temperature decreases. However the NF decreases with increasing the length. Furthermore, the NF increases when the temperature rises.

We have analyzed the noise performance in EDFAs and PDFAs under different operating conditions. When comparing the two models, It is clear that the NF for the both the EDFA and PDFAs increases with temperature. However, for the




Fig. 3. Temperature-dependent noise figure analysis (the change of noise figure via erbium-doped fiber length in the spectral contribution of copropagating ASE power of 0.15 mW and when  $P_p^i(0) = 30$  mW and  $P_s(0) = 10$   $\mu$ W).




Fig. 4. The change of the noise figure with temperature and length of ZBLAN based  $\text{Pr}^{3+}$ -doped fiber amplifier for a signal input power of -30 dBm and pump power of 20 dBm.




Fig. 5. The change of the noise figure with temperature and length of GeGa-sulfide based  $\text{Pr}^{3+}$ -doped fiber amplifier for a signal input power of -30 dBm and pump power of 20 dBm.

EDFA amplifier there is no variation of NF with temperature for lengths below 6 m. This can be explained by the fact that the population inversion ratio is very low. For any further

increase in length it can be seen that NF increases with temperature, at the same time the NF stays almost constant with any further increase in the length. On the other hand, for the PDFA, the NF increases with increasing the temperature, at the same time, the NF decreases with increasing the length. This is due to the Boltzmann distribution change. PDFA amplifier, being a four-level system, the noise figure can be easily obtained compared with EDFA. The NF performance of the PDFA is comparable with that of EDFA. However the NF in EDFA is more sensitive to operating conditions at peak wavelengths, while PDFA it is not sensitive to operating conditions. We found that the NF is strongly signal wavelength dependent due to lower population inversion in EDFAs and due to ground state absorption (GSA) in PDFAs. We have confirmed that the NF is independent of numerical aperture (NA) for both amplifiers.

#### IV. CONCLUSION

The erbium-doped fiber amplifier is an attractive candidate for 1530 nm systems because of its very low noise and high gain, while praseodymium-doped fiber amplifier is for 1300 nm systems. The two models have been introduced as simple schematic representations for energy levels and amplification mechanisms (Two levels for  $\text{Er}^{3+}$  and four levels for  $\text{Pr}^{3+}$ ). The basic rate equation models have been carried out, including the temperature effect to obtain the signal noise figure of the erbium and praseodymium-doped fiber amplifiers at research level. Moreover, we have shown the possibility of obtaining an analytical solution of the rate equations in some practical temperature ranges to comprehend the noise figure of both fiber amplifiers.

#### REFERENCES

- [1] J. Kemtchou, M. Duhamel, P. Lecoy, "Gain temperature dependence of erbium-doped silica and fluoride fiber amplifiers in multichannel wavelength-multiplexed transmission systems", *IEEE J. Lightwave Technol.* 15 (11), pp. 2083-2090, 1997.
- [2] M. Peroni, M. Tamburrini, "Gain in erbium-doped fiber amplifiers: A simple analytical solution for the rate equations", *Opt. Lett.*, 15(15), pp. 842 - 844, 1990.
- [3] N. Kagi, A. Oyobe, K. Nakamura, "Temperature dependence of the gain in erbium-doped fibers", *IEEE J. Lightwave Technol.* 9 (2), pp. 261-265, 1991.
- [4] C. Berkdemir, S. Özsoy, "On the Temperature-Dependent Gain and Noise Figure Analysis of C-Band High-Concentration EDFAs with the Effect of Cooperative Upconversion", *Journal of Lightwave Technology*, 27 (9), pp. 1122-1127, 2009.
- [5] K. Furusawa, T.M. Monro, D.J. Richardson, "High gain efficiency amplifier based on an erbium doped aluminosilicate holey fiber", *Opt. Express*, 12 (15), pp. 3452-3458, 2004.
- [6] M. Yamada, M. Shimizu, M. Horiguchi, M. Okayasu, "Temperature dependence of signal gain in  $\text{Er}^{3+}$ -doped optical fiber amplifiers", *IEEE J. Quantum Electron.*, 28 (3), pp. 640-649, 1992.
- [7] Y. Ohishi et al., "Pr<sup>3+</sup>-doped fluoride fiber amplifier operating at 1.31  $\mu\text{m}$ ", *Opt. Lett.* 16 (22), pp. 1747-1749, 1991.
- [8] G. Lawton, "Optical Amplifiers Technology and System", IGI Publisher, 1999.
- [9] Y. Ohishi et al., OFC91, Postdeadline Paper PD2, (1991)
- [10] Y. Miyajima et al., Top. Meet. Opt. Amp. Appl., Postdeadline Paper PD1, 1991.

- [11] B. Pedersen, W.J. Miniscalco, R.S. Quimby, "Optimization of Pr<sup>3+</sup>:ZBLAN fiber amplifiers", *IEEE Photon. Technol. Lett.*, 4 (5), pp. 446-448, 1992.
- [12] S.H. Yuan, *J. Non-Cryst. Solids* 215, 1997, 108.
- [13] K. Itoh et al., *J. Non-Cryst. Solids*, pp. 256-257, 1999, 1.
- [14] D.R. Simons, A.J. Faber, H. de Waal, "Pr<sup>3+</sup>-doped GeS<sub>x</sub>-based glasses for fiber amplifiers at 1.3 μm," *Opt. Lett.*, 20 (5), pp. 468-470, 1995.
- [15] P. Sirivastava, S.B. Rai, D.K. Rai, "Effect of lead oxide on optical properties of Pr(3+) doped some borate based glasses" , *J. Alloys Compd.* 368. 1-7 ,2004.
- [16] E. Desurvire, "Erbium-Doped fiber Amplifiers; Principle and Applications" (John Wiley and Sons. Inc, New York, 1994.
- [17] C. Berkdemir, S. Ozsoy, "Modelling consideration of praseodymium-doped fiber amplifiers for 1.3μm wavelength applications", *Opt. Commun.* 269, pp. 102-106, 2007.
- [18] A. Yariv, *Quantum Electronics*, Third Edition, John Wiley, New York, 1988, 220.
- [19] W.J. Miniscalco, R. S. Quimby, "General procedure for the analysis of Er<sup>3+</sup> cross sections", *Opt. Lett.*, 16 (4), pp. 258-260, 1991.
- [20] P. C. Becker, N. Olsson, J. Simpson, "Erbium -Doped Fiber Amplifiers: Fundamentals and Technology", Academic Press, San Diego, (Copyright by Lucent Technologies) 1999.
- [21] M. C. Lin, and S. Chi, "The Gain and Optimal Length in the Erbium-Doped Fiber Amplifiers with 1480 nm Pumping" *IEEE Photonics Tech. Lett.* 4 (4), pp. 354-356, 1992.
- [22] D. R. Simons, Eindhoven University of Technology Research Reports, ISBN 90-386-0496-3, Nov. 1995.
- [23] Ohishi, T. Kanamori, Y. Terunuma, M. Shimizu, M. Yamada, and S. Sudo, "Investigation of efficient pump scheme for Pr<sup>3+</sup> doped fluoride fiber amplifiers", *IEEE Photon. Technol. Lett.*, (6), pp. 195 - 198, 1994.